PCT

(22) International Filing Date:

08/701,483

(30) Priority Data:

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

US

28 March 1997 (28.03.97)

(71) Applicant: RESEARCH TRIANGLE PHARMACEUTICALS
LTD. [US/US]; 4364 South Alston Avenue, Durham, NC

22 August 1996 (22.08.96)

27713-2280 (US).
(72) Inventors: PARIKH, Indu; 2558 Booker Creek Road, Chapel

Hill, NC 27514 (US). SELVARAJ, Ulagaraj; 5323-C Penrith Drive, Durham, NC 27713 (US).

(74) Agent: CRAWFORD, Arthur, R.; Nixon & Vanderhye P.C., 8th floor, 1100 North Glebe Road, Arlington, VA 22201-4714 (US). BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).

Published

With international search report.

Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.

(54) Title: COMPOSITIONS COMPRISING MICROPARTICLES OF WATER-INSOLUBLE SUBSTANCES AND METHOD FOR PREPARING SAME

(57) Abstract

Submicron size particles of pharmaceutical or other water-insoluble or poorly water-insoluble substances are prepared using a combination of one or more surface modifiers/surfactants such as polaxomers, poloxamines, polyoxyethylene sorbitan fatty acid esters and the like together with natural or synthetic phospholipids. Particles so produced have a volume weighted mean particle size at least one-half smaller than obtainable using a phospolipid alone. Compositions so prepared are resistant to particle size growth on storage.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	ĹIJ	Luxembourg	SN	Senegal
ΑU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JР	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
СН	Switzerland	KG	Kyrgyzstan	NO	Norway	2W	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	ıc	Saint Lucia	RU	Russian Federation		
DE	Germany	u	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

.

1

COMPOSITIONS COMPRISING MICROPARTICLES OF WATER-INSOLUBLE SUBSTANCES AND METHOD FOR PREPARING SAME

This invention relates to compositions and procedures that yield sub-micron and micron stable particles of water-insoluble or poorly soluble drugs or other industrially useful insoluble compounds. The compositions of this invention include combinations of natural or synthetic phospholipds, and one or more non-ionic, anionic or cationic surfactants coated or adhered onto the surfaces of the water insoluble-compound particles. The combination of phospholipids and surfactants allows the formation and stabilization of the sub-micron and micron size compound particles via hydrophilic, lipophilic and electrostatic interactions and therefore prevent these particles from aggregation or flocculation.

15

BACKGROUND OF THE INVENTION

There is a critical need in the pharmaceutical and other biological based industries to formulate water-insoluble or poorly soluble substances into formulations for oral, injectable, inhalation and ophthalmic routes of delivery. Water insoluble compounds are those having poor solubility in water, that is < 5 mg/ml at physiological pH (6.5-7.4). Preferably their water solubility is < 1 mg/ml, more preferably < 0.1 mg/ml. It is desirable that the drug is stable in water as a dispersion; otherwise a lyophilized or spray-dried solid form may be desirable.

2

As used herein, "micro" refers to a particle having diameter of from nanometers to micrometers. Microparticles, as used herein, refer to solid particles of irregular, non-spherical or spherical shapes. Formulations containing these microparticles provide some specific 5 advantages over the unformulated non-micronized drug particles, which include improved oral bioavailability of drugs that are poorly absorbed from GI tract, development of injectable formulations that are currently available only in oral dosage form, less toxic injectable formulations that are currently prepared with organic solvents. sustained release of intramuscular injectable drugs that are currently administered through daily injection or constant infusion, and preparation of inhaled, ophthalmic formulation of drugs that otherwise could not be formulated for nasal or ocular use.

Current technology for delivering insoluble drugs as described in US Patents 5,091,188; 5,091,187 and 4,725.442 focuses on (a) either coating small drug particles with natural or synthetic phospholipds or (b) dissolving the drug in a suitable lipophilic carrier and forming an emulsion stabilized with natural or semisynthetic 20 phospholipids. One of the disadvantages of these formulations is that certain drug particles in suspension tend to grow over time because of the dissolution and reprecipitation phenomenon known as the "Oswald ripening".

DESCRIPTION OF THE INVENTION

25

15

The present invention focuses on preparing submicron size particles using a combination of surface modifier(s) with a phospholipid, and how the growth of particle size, and hence storage stability, is

3

controlled by adding a combination of surface modifier(s) with a phospholipid to the formulation.

The use of a surface modifier or combination of surface

modifiers in addition to a phospholipid is characterized by its ability to result in volume weighted mean particle size values that are (i) at least 50% and preferably about 50-90% smaller than what can be achieved using phospholipid alone without the use of a surfactant with the same energy input, and (ii) provide compositions resistant to particle size growth on storage. While resistance to particle size growth on storage was an objective of this invention we were surprised to observe a significant reduction in particle size with the addition of the surfactant. In order to achieve the advantages of the present invention it is necessary that the phospholipid and the surfactant both be present at the time of particle size reduction or precipitation.

Although we do not wish to be bound by any particular theory, it appears that these surface modifiers generally, that is phospholipids and one or more surfactants, adsorb to the surfaces of drug particles. and (a) convert lipophilic to hydrophilic surfaces with increased steric hindrance/stability, and (b) possibly modify zeta potential of surfaces with more charge repulsion stabilization. The concentrations of surface modifiers used in the process described here are normally above their critical micelle concentrations (CMC) and hence facilitate the formation of sub-micron particles by stabilizing the particles.

Phospholipid and surface modifier(s) are adsorbed on to the surfaces of drug particles in sufficient quantity to retard drug particle growth, reduce drug average particle size from 5 to 100 µm to submicron and micron size particles by one or combination of methods known in the art, such as sonication, homogenization, milling, microfluidization, precipitation or recrystallization or precipitation from supercritical fluid, and maintain sub-micron and micron size particles on subsequent storage as suspension or solid dosage form.

The concentration of phospholipid or surface modifier in the suspension or solid dosage form can be present in the range of 0.1 to 50%, preferably 0.2 to 20%, and more preferably 0.5 to 10%.

The formulations prepared by this invention may be lyophilized into powders, which can be resuspended or filled into capsules or converted into granules or tablets with the addition of binders and other excipients known in the art of tablet making.

By industrially useful insoluble or poorly soluble compounds
we include biologically useful compounds, imaging agents,
pharmaceutically useful compounds and in particular drugs for human
and veterinary medicine. Water insoluble compounds are those
having a poor solubility in water, that is less than 5 mg/ml at a
physiological pH of 6.5 to 7.4, although the water solubility may be
less than 1 mg/ml and even less than 0.1 mg/ml.

Examples of some preferred water-insoluble drugs include immunosuppressive and immunoactive agents, antiviral and

5

antifungal agents, antineoplastic agents, analgesic and antiinflammatory agents, antibiotics, anti-epileptics, anesthetics,
hypnotics, sedatives, antipsychotic agents, neuroleptic agents,
antidepressants, anxiolytics, anticonvulsant agents, antagonists,
neuron blocking agents, anticholinergic and cholinomimetic agents,
antimuscarinic and muscarinic agents, antiadrenergic and
antarrhythmics, antihypertensive agents, antineoplastic agents,
hormones, and nutrients. A detailed description of these and other
suitable drugs may be found in *Remington's Pharmaceutical Sciences*.

18th edition, 1990, Mack Publishing Co. Philadelphia, PA.

The phospholipid may be any natural or synthetic phospholipid. for example phosphatidylcholine, phosphatidylethanolamine, phosphatidylserine, phosphatidylinositol, phosphatidylglycerol.

15 phosphatidic acid, lysophospholipids, egg or soybean phospholipid or a combination thereof. The phospholipid may be salted or desalted, hydrogenated or partially hydrogenated or natural semisynthetic or synthetic.

Examples of some suitable second surface modifiers include:

(a) natural surfactants such as casein, gelatin, tragacanth. waxes, enteric resins, paraffin, acacia, gelatin, cholesterol esters and triglycerides, (b) nonionic surfactants such as polyoxyethylene fatty alcohol ethers, sorbitan fatty acid esters, polyoxyethylene fatty acid esters, sorbitan esters, glycerol monostearate, polyethylene glycols. cetyl alcohol, cetostearyl alcohol, stearyl alcohol, poloxamers, polaxamines, methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline

cellulose, polyvinyl alcohol, polyvinylpyrrolidone, and synthetic phospholipids, (c) anionic surfactants such as potassium laurate, triethanolamine stearate, sodium lauryl sulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, negatively charged phospholipids (phosphatidyl glycerol, phosphatidyl inosite, phosphatidylserine, phosphatidic acid and their salts), and negatively charged glyceryl esters, sodium carboxymethylcellulose, and calcium carboxymethylcellulose, (d) cationic surfactants such as quaternary ammonium compounds, benzalkonium chloride,

cetyltrimethylammonium bromide, chitosans and lauryldimethylbenzylammonium chloride, (e) colloidal clays such as bentonite and veegum. A detailed description of these surfactants may be found in Remington's Pharmaceutical Sciences, and Theory and Practice of Industrial Pharmacy, Lachman et al. 1986.

15

More specifically, examples of suitable second surface modifiers include one or combination of the following: polaxomers, such as PluronicTM F68, F108 and F127, which are block copolymers of ethylene oxide and propylene oxide available from BASF, and poloxamines, such as TetronicTM 908 (T908), which is a tetrafunctional block copolymer derived from sequential addition of ethylene oxide and propylene oxide to ethylene-diamine available from BASF, TritonTM X-200, which is an alkyl aryl polyether sulfonate, available from Rohm and Haas. Tween 20, 40, 60 and 80, which are polyoxyethylene sorbitan fatty acid esters, available from ICI Speciality Chemicals, CarbowaxTM 3550 and 934, which are polyethylene glycols available from Union Carbide, hydroxy propylmethylcellulose, dimyristoyl phosphatidylglycerol sodium salt,

7

sodium dodecylsulfate, sodium deoxycholate, and cetyltrimethylammonium bromide.

It is thought that some of the functions of the second surface

modifier(s) as it relates to this invention are suppressing the process
of Oswald Ripening and therefore maintaining the particle size,
increasing the storage stability, minimizing sedimentation, and
decreasing the particle growth during lyophilization and
reconstitution; adhere or coat firmly onto the surfaces of
water-insoluble drug particles and therefore modify the interfaces
between the particles and the liquid in the resulting formulations;
increase the interface compatibility between water-insoluble drug
particles and the liquid; and possibly to orient preferentially
themselves with the hydrophilic portion sticking into the aqueous
solution and the lipophilic portion strongly adsorbed at the
water-insoluble drug particle surfaces

Considerable variations as to the identities and types of phospholipid and especially the surface active agent or agents should be expected depending upon the drug or active agent selected as the surface properties of these small particles are different. The most advantageous surface active agent for the insoluble drug will be apparent following empirical tests to identify the surfactant or surfactant system/combination resulting in the requisite particle size and particle size stability on storage over time.

Various procedures can be used to produce these stable sub-micron and micron size particles including mixing the insoluble

substance with phospholipid and precipitating from a dissolved mixture of the substance, phospholipid and surfactant using other surfactants followed by sonication, milling, homogenization, microfluidization, and antisolvent and solvent precipitation. Mannitol and other agents may be added to adjust the final formulation to isotonicity as well as a stabilizing aid during drying.

Unless otherwise specified, all parts and percentages reported herein are weight per unit volume (w/v), in which the volume in the denominator represents the total volume of the system. Diameters of dimensions are given in millimeters (mm = 10⁻³ meters), micrometers (µm = 10⁻⁶ meters), nanometers (nm = 10⁻⁹ meters) or Angstrom units (= 0.1 nm). Volumes are given in liters (L), milliliters (mL = 10⁻³ L) and microliters (µL = 10⁻⁶L). Dilutions are by volume. All temperatures are reported in degrees Celsius. The compositions of the invention can comprise, consist essentially of or consist of the materials set forth and the process or method can comprise, consist essentially of or consist

The following examples further explain and illustrate the invention:

Example 1

25 Microparticle-cyclosporine, of an immunosuppressive drug. was prepared as follows. The composition and concentration of excipients of the microparticle cyclosporine formulation are listed below:

9

Cyclosporine	50 mg/ml
Egg Phosphatidylcholine	100 mg/ml
Mannitol	55 mg/ml
Tween 80	10 mg/ml
Distilled Water	qs to 100%
Total Volume	20 ml

5

Cyclosporine with an average particle size from 5-100 µm, and mannitol were purchased from Sigma, egg phosphatidylcholine was produced by Pfanstiehl, Tween 80 was purchased from ICI.

The above components were placed in a 30 ml beaker and pre-mixed with a hand-held biohomogenizer (Honeywell DR 4200 model GP) for 1-5 min. During homogenization, dilute NaOH was added to the pre-mix to adjust the pH from 3.1 to 7 ± 0.5 . The pre-mix was placed in a water jacketed vessel (50 ml capacity) through which thermostated water at 4°C was circulated to control the temperature of the formulation. The pre-mix was subjected to high shear energy of a probe sonicator (Fisher, model 550 Sonic 20 Dismembrator) with a 0.5 inch diameter probe. Sonic pulses of 10 seconds at 10-seconds intervals at a power setting of 5 were utilized. During sonication the temperature of the formulation was 18 ± 2 °C. The pH during sonication was adjusted to 7 ± 0.5 with dilute NaOH. Total sonication time employed to prepare the microparticle cyclosporine was usually 10.5 hours or less. The microparticlecyclosporine formulation was placed in 20 ml vials and stored at 4 and 25°C for further stability studies.

Particle size distribution of the suspension was analyzed with a NICOMP model 370 Particle Size Analyzer. This instrument utilizes photon correlation spectroscopy for particle sizing in the submicron region. A small volume of the suspension was diluted with water and 5 placed in the cell of the particle size analyzer. Particle size determination based on volume weighted and number weighted particle size determination of the suspension, represented as a Gaussian distribution by the NICOMP 370 software, yielded the mean particle size values, which are listed below in Table I.

10

Table I: Volume-and Number-weighted Particle Size Stability of Microparticle-Cyclosporine

15 Storage		Storage at 4°C		Storage at 25°C	
	Time	Mean Particle Size (nm)		Mean Particle Size (nn	
	Days	Volume-	Number-	Volume-	Number-
		Weighted	Weighted	Weighted	Weighted
	0	361	63	361	63
	7	337	69	423	67
20	51	358	76	455	66 .

20

Approximately 20 µl of the freshly prepared suspension was placed on a clean slide, with a clean cover glass, and examined under 25 an Olympus BH2 microscope with 1000X magnification. An eye-piece equipped with a graticule was used to estimate the particle size. Most of the particles in the suspension were 0.3-0.5 µm.

11

Furthermore, microscopic examination of the suspension confirmed non-agglomerated or flocculated micron and sub-micron size drug particles exhibiting Brownian motion.

Example 2

For purpose of comparison (not according to the invention) using only a phospholipid, microparticle-cyclosporine with lecithin alone (without the second surface modifier, Tween 80) was also prepared using the same procedure as Example 1. The suspension was stored in 20 ml glass vials for storage stability studies. The volume and number weighted mean particle size values of the suspension stored at 4 and 25°C are listed below. The results in Table II illustrate that the presence of lecithin alone (without the presence of Tween 80) does not provide the particle size reduction and enhancement in storage stability as described in Example 1.

Table II: Volume-weighted Particle Size Stability of Microparticle-Cyclosporine

20

5

Storage	Storage	e at 4°C	Storage at 25°C		
Time	Mean Particle Size (nm)		Mean Particle Size (nm)		
Days	Days Volume-		Volume-	Number-	
	Weighted	Weighted	Weighted	Weighted	
0	704	91	704	91	
1	1472	503	2230	755	
6	1740	416	2290	874	

12

Example 3

For purpose of comparison (not according to the invention)
using only a surface modifier, microparticle-cyclosporine with Tween
80 alone (without a phospholipid, egg phosphatidylcholine) was also
prepared using the same procedure as Example 1. The suspension
was stored in 20 ml glass vials. The results in Table III illustrate that
the presence of Tween 80 alone (without the presence of phospholipid
does not provide particle size reduction as in Example 1.

Table III: Volume- and Number-weighted Particle Size Stability of Microparticle-Cyclosporine

	Mean Particle Size (nm)						
	Day Volume-Weighted Number-Weigh						
15	0	521	67				

Example 4

The following microparticle-Docosanol formulations were prepared by the process of the invention with Tween 80, Tween 20, egg phosphatidylcholine, and/or Phospholipon 90H as surface modifiers. Docosanol is available from Sigma. The formulations were prepared according to the procedures of Example 1. The compositions and concentration of excipients of the microparticle formulations are listed below:

25

Microparticle-Docosanol (Example 4.1, comparative)

	Docosanol	20 mg/ml
	Egg Phosphatidylcholine	50 mg/ml
5	Mannitol	55 mg/ml
	Distilled Water	qs to 100%
	Total Volume	20 ml

Microparticle-Docosanol (Example 4.2)

10

	Docosanol	20 mg/ml
	Egg Phosphatidylcholine	50 mg/ml
	Mannitol	55 mg/ml
	Tween 80	10 mg/ml
15	Distilled Water	qs to 100%
	Total Volume	20 ml

Microparticle-Docosanol (Example 4.3)

	Docosanol	20 mg/ml
	Egg Phosphatidylcholine	50 mg/ml
	Mannitol	55 mg/ml
	Tween 20	10 mg/ml
25	Distilled Water	qs to 100%
	Total Volume	20 ml

Microparticle-Docosanol (Example 4.4)

	Docosanol	20 mg/ml
	Phospholipon 90H	30 mg/ml
5	Mannitol	55 mg/ml
	Tween 80	10 mg/ml
	Distilled Water	qs to 100%
	Total Volume	20 ml

10 Microparticle-Docosanol (Example 4.5, Comparative)

	Docosanol	20 mg/ml
	Mannitol	55 mg/ml
	Tween 80	10 mg/ml
15	Distilled Water	qs to 100%
	Total Volume	20 ml

The mean volume-and number-weighted particle size values of the suspension were 286 nm, and 98 nm, respectively.

20

The volume weighted mean particle size values of the above suspension stored at 4°C are listed below in Table IV.

15

Table IV: Volume-weighted and Number Weighted
Particle Size Stability of Microparticle-Docosanol Stored at 4°C.

5	Storage	(Example 4.1) Mean Particle Size (nm)		(Example 4.2) Mean Particle Size (nm)	
	Time				
	Days	Volume-	Number-	Volume-	Number-
		Weighted	Weighted	Weighted	Weighted
	0	688		112	55
	30	ND	ND	156	81

10

Storage	(Exam	ple 4.3)	(Example 4.4)	
Time	Mean Particle Size (nm)		Mean Particle Size (nm)	
Days	Volume- Weighted	Number- Weighted	Volume- Weighted	Number- Weighted
0	129	61	90	35
30	184	99	127	39

15

ND = Not Determined

20

The above data illustrate the much smaller particles produced by the present invention with the presence of a surfactant in addition to the phospholipid and that these particles retain their particle size over time without significant increase in size.

Example 5

The following seven microparticle-RTP-4055 (an antiviral drug) formulations were prepared with combinations of Tween 80,

5 Tetronic 908, Pluronic F-68, egg phosphatidylcholine, and/or phospholipon 90H as surface modifiers. The details of the sonication method are similar to those discussed in Example 1. The compositions and concentration of excipients of the microparticle formulations are listed below:

10

15

Microparticle-RTP-4055 (Example 5.1, Comparative)

RTP-4055	50 mg/ml
Egg Phosphatidylcholine	50 mg/ml
Distilled Water	qs to 100%
Total Volume	25 ml

The mean volume weighted particle size of the suspension was 3195 nm.

20

Microparticle-RTP-4055 (Example 5.2)

•	RTP-4055	50 mg/ml
	Egg Phosphatidylcholine	50 mg/ml
25	Mannitol	55 mg/ml
	Pluronic F-68	5 mg/ml
	Distilled Water	qs to 100%
	Total Volume	25 ml

17

The mean volume- and number-weighted particle size values of the suspension were 672 nm and 76 nm respectively.

5 Microparticle-RTP-4055 (Example 5.3)

	RTP-4055	50 mg/ml
	Egg Phosphatidylcholine	50 mg/ml
	Mannitol	55 mg/ml
10	Tetronic 908	5 mg/ml
	Distilled Water	qs to 100%
	Total Volume	25 ml

The mean volume- and number- weighted particle size values of the suspension were 436 nm and 59 nm respectively.

Microparticle-RTP-4055 (Example 5.4, Comparative)

	RTP-4055	50 mg/ml
20	Phospholipon 90H	30 mg/ml
	Distilled Water	qs to 100%
	Total Volume	25 ml

The mean volume- number- weighted particle size values of the suspension were 1117 nm. and 108 nm respectively.

18

Microparticle-RTP-4055 (Example 5.5)

	RTP-4055	50 mg/ml
	Phospholipon 90H	30 mg/ml
5	Mannitol	55 mg/ml
	Dimyristoylphosphatidyl	
	choline (DMPG)	3 mg/ml
	Tween 80	10 mg/ml
	Distilled Water	qs to 100%
10	Total Volume	25 ml

The mean volume weighted particle size of the suspension was 236 nm. The particle size of the suspension stored at 4°C for 1 week and 1 month are 328 and 397 nm, respectively, which indicates the stability of the suspension.

Microparticle-RTP-4055 (Example 5.6)

	RTP-4055	50 mg/ml
20	Phospholipon 90H	30 mg/ml
	Mannitol	55 mg/ml
	Tween 80	10 mg/ml
	Distilled Water	qs to 100%
	Total Volume	25 ml

25

The mean volume- and number- weighted particle size values of the suspension were 382 nm and 59 nm respectively. Within the

19

error limits, there was no variation in the mean particle size after one week of storage at 4°C.

Microparticle-RTP-4055 (Example 5.7, Comparative)

5

10

RTP-4055	50 mg/ml
Mannitol	55 mg/ml
Tween 80	10 mg/ml
Distilled Water	qs to 100%
Total Volume	25 ml

The volume- and number-weighted mean particle size values of the suspension were 545 nm, and 75 nm, respectively within the error limits, there was no variation in the mean particle size after one week of storage at 4°C.

Example 6

The following six microparticle-Piroxicam formulations were prepared with combination of Tween 80, Tetronic 908, Pluronic F-68, and/or egg phosphatidylcholine as surface modifiers. Piroxicam was received from Cipla. The details of the sonication method are similar to those discussed in example 1. The compositions and concentration of excipients of the microparticle formulations are listed below:

Microparticle-Piroxicam (Example 6.1)

	Piroxicam	67 mg/ml
	Egg Phosphatidylcholine	67 mg/ml
5	Mannitol	67 mg/ml
	Tween 80	5 mg/ml
	Tetronic 908	5 mg/ml
	Distilled Water	qs to 100% (w/v)
	Total Volume	15 ml

10

The mean volume- and number- weighted particle size values of the suspension were 674 nm and 72 nm respectively.

Microparticle-Piroxicam (Example 6.2)

15

10		
	Piroxicam	67 mg/ml
	Egg Phosphatidylcholine	67 mg/ml
	Mannitol	67 mg/ml
	Tetronic 908	5 mg/ml
20	Distilled Water	qs to 100% (w/v)
	Total Volume	15 ml

The mean volume- and number- weighted particle size values of the suspension were 455 nm and 58 nm respectively.

Microparticle-Piroxicam (Example 6.3)

Piroxicam 67 mg/ml
Egg Phosphatidylcholine 67 mg/ml
Mannitol 67 mg/ml
Pluronic F-68 5 mg/ml
Distilled Water qs to 100% (w/v)
Total Volume 15 ml

The mean volume- and number- weighted particle size values of the suspension were 564 nm and 68 nm respectively.

Microparticle-Piroxicam (Example 6.4)

15	Piroxicam	67 mg/ml
	Egg Phosphatidylcholine	67 mg/ml
	Mannitol	67 mg/ml
	Tween 80	5 mg/ml
2 0	Cetyltrimethylammonium bromide	10 mg/ml
	Distilled Water	qs to 100% (w/v)
	Total Volume	15 ml

The mean volume- and number- weighted particle size values of the suspension were 479 nm and 80 nm respectively.

22

Microparticle-Piroxicam (Example 6.5)

	Piroxicam	67 mg/ml
	Egg Phosphatidylcholine	67 mg/ml
5	Mannitol	67 mg/ml
	Cetyltrimethylammonium bromide	10 mg/ml
	Distilled Water	qs to 100% (w/v)
10	Total Volume	15 ml

The mean volume- and number- weighted particle size values of the suspension were 670 nm and 128 nm respectively.

15 Microparticle-Piroxicam (Example 6.6, Comparative)

	Piroxicam	67 mg/ml
	Mannitol	67 mg/ml
	Tween 80	5 mg/ml
20	Tetronic 908	5 mg/ml
	Distilled Water	qs to 100%
	Total Volume	25 ml

The volume- and number- weighted particle size values of the suspension were 1184 nm and 385 nm, respectively.

WHAT IS CLAIMED IS:

- 3 1. A composition of microparticles of a water-insoluble
- 4 substance comprising particles of an industrially useful water-
- insoluble or poorly soluble compound, a phospholipid and at least one
- 6 non-ionic, anionic or cationic surfactant, in which the surfactant or
- 7 surfactants provide volume-weighted mean particle size values of the
- 8 water-insoluble compound at least 50% smaller than particles
- 9 produced without the presence of the surfactant using the same energy
- 10 input.
 - 2. A pharmaceutical composition of microparticles of a water-
 - 2 insoluble substance comprising particles of an industrially useful
 - 3 water-insoluble or poorly soluble compound, a phospholipid and at
 - 4 least one non-ionic, anionic or cationic surfactant, in which the
 - 5 surfactant or surfactants provide volume-weighted mean particle size
 - 6 values of the water-insoluble compound at least 50% smaller than
 - 7 particles produced without the presence of the surfactant using the
 - 8 same energy input.
 - 3. The pharmaceutical composition of claim 2 for oral,
- 2 inhalation, ocular, nasal or injectable administration.
- 4. The pharmaceutical composition of claim 3 in injectable
- form for intravenous, intra-arterial, intra-muscular, intradermal,
- 3 subcutaneous, intra-articular, cerebrospinal, epidural, intracostal,
- 4 intraperitoneal, intratumor, intrabladder, intra-lesion or
- 5 subconjunctival administration.

5 6

7

combinations thereof.

1	5. A dried suspension of the composition of claim 4 which can
2	be resuspended in aqueous or non-aqueous media.
1	6. A suspension, spray-dried powder, lyophilized powder
2	granules or tablets of the composition of claim 2.
1	7. A composition of claim 1 in which the water-insoluble
2	compound is a biologically useful compound or an imaging agent.
1	8. The composition of claim 1 or claim 2 wherein the
2	surfactant is a polyoxyethylene sorbitan fatty acid ester, a block
3	copolymer of ethylene oxide and propylene oxide, a tetrafunctional
4	block copolymer derived from sequential addition of ethylene oxide
5	and propylene oxide to ethylenediamine, an alkyl aryl polyether
6	sulfonate, polyethylene glycol, hydroxy propylmethylcellulose,
7	sodium dodecylsulfate, sodium deoxycholate,
8	cetyltrimethylammonium bromide or combinations thereof.
1	9. The process of claim 1 or 2 wherein the phospholipid is of
2	egg or plant origin or semisynthetic or synthetic in partly or fully
3	hydrogenated form or in a desalted or salt form such as

phosphatidylcholine, phospholipon 90H or dimyristoyl

phosphatidylglyerol sodium salt, phosphatidylethanolamine,

phosphatidylserine, phosphatidic acid, lysophospholipids or

1	10. A process for preparing sub-micron and micron sized,
2	stable particles of water-insoluble or a poorly soluble industrially
3	useful compound using natural or synthetic phospholipids, said
4	process comprising reducing the particle size by sonication,
5	homogenization, milling, microfluidization and precipitation, or
6	recrystallization and precipitation of the compound using antisolvent
7	and solvent precipitation including from supercritical fluids in the
8	presence of a phospholipid and at least one non-ionic, anionic or
9	cationic surfactant.

- 11. A process of preparing microparticles of a water-insoluble or poorly soluble compound comprising the steps of:
- (1) mixing particles of a water-insoluble or poorly soluble industrially useful compound with a phospholipid and at least one non-ionic, anionic or cationic surfactant, and thereafter
- (2) applying energy to the mixture sufficient to produce volume-weighted mean particle size values of the compound at least 50% smaller than particles produced without the presence of the surfactant using the same energy input.
- 12. The process of claim 10 or 11 wherein the phospholipid is of egg or plant origin or semisynthetic or synthetic in partly or fully hydrogenated form or in a desalted or salt form such as phosphatidylcholine, phospholipon 90H or dimyristoyl phosphatidylglyerol sodium, salt, phosphatidylethanolamine, phosphatidiylserine, phosphatidic acid, lysophospholipids, or
- 7 combinations thereof.

2

process of claim 11.

13. The process of claim 10 or 11 wherein the surfactant is a polyoxyethylene sorbitan fatty acid ester, a block copolymer of ethylene oxide and propylene oxide, a tetrafunctional block copolymer derived from sequential addition of ethylene oxide and propylene oxide to ethylenediamine, an alkyl aryl polyether sulfonate, polyethylene glycol, hydroxy propylmethylcellulose, sodium dodecylsulfate, sodium deoxycholate, cetyltrimethylammonium
ethylene oxide and propylene oxide, a tetrafunctional block copolymer derived from sequential addition of ethylene oxide and propylene oxide to ethylenediamine, an alkyl aryl polyether sulfonate, polyethylene glycol, hydroxy propylmethylcellulose, sodium
copolymer derived from sequential addition of ethylene oxide and propylene oxide to ethylenediamine, an alkyl aryl polyether sulfonate, polyethylene glycol, hydroxy propylmethylcellulose, sodium
propylene oxide to ethylenediamine, an alkyl aryl polyether sulfonate, polyethylene glycol, hydroxy propylmethylcellulose, sodium
polyethylene glycol, hydroxy propylmethylcellulose, sodium
dodecylsulfate sodium doornal at a second at a
dodecy isulfate, sodium deoxycholate, cetyltrimethylammonium
bromide or combinations thereof.
14. The process of claim 10 or 11 wherein the surfactant is present above the critical micelle concentration.
15. The process of claim 10 or 11 in which the compound is a
biologically useful compound or an imaging agent.

17. A composition comprising microparticles produced by the

International Application No PCT/US 97/04695

A. CLAS	SIFICATION OF SUBJECT MATTER A61K9/51 A61K9/14 A61K49/	′04		
According	to Infernational Patent Classification (IPC) or to both national classific	cation and IPC		
B. FIELD	S SEARCHED			
Minimum 6	documentation searched (classification system followed by classification A61K	ilon symbols)		
	ation searched other than minimum documentation to the extent that .			
Electronic	data base consulted during the international search (name of data b	ase and, where practical, search terms used		
C. DOCUA	MENTS CONSIDERED TO BE RELEVANT			
Category *	Citation of document, with indication, where appropriate, of the re	levant passages	Relevant to claim No.	
x	EP 0 601 618 A (STERLING WINTHRO June 1994 see the whole document	P INC) 15	1-4, 6-13, 15-17	
X	EP 0 602 700 A (STERLING WINTHROP INC) 22 June 1994 see the whole document US 5 447 710 A (NA GEORGE C ET AL) 5 September 1995 see the whole document		1-4,6-9	
X			1-4,6-9	
X	US 5 326 552 A (NA GEORGE C ET 1994 see the whole document	AL) 5 July	1-4,6-9	
		-/		
X Fun	her documents are listed in the continuation of box C.	X Patent family members are listed in	n annex.	
* Special ca	tegories of cited documents :	"T" later document published after the inter	national filling data	
	ont defining the general state of the art which is not ered to be of particular relevance	or priority date and not in conflict with cited to understand the principle or the invention	the application but	
"E" earlier o	document but published on or after the international late	"X" document of particular relevance; the coannot be considered novel or cannot	laimed invention	
which	nt which may throw doubts on priority claim(s) or is cited to establish the publication date of a nother to or other special reason (as specified)	involve an inventive step when the doc "Y" document of particular relevance; the ci	cument is taken alone almed invention	
	ent referring to an oral disclosure, use, exhibition or	cannot be considered to involve an inv document is combined with one or mo ments, such combination being obviou	rentive step when the re other such docu-	
"P" docume	nt published prior to the international riling date but an the pnority date claimed	in the art. "6." document member of the same patent f		
Date of the	actual completion of theinternational search	Date of mailing of the international sear	ch report	
2	December 1997	15/12/1997		
Name and m	nailing address of the ISA European Patent Office, P.B. 5818 Patentiaan 2	Authorized officer		
	NL ~ 2280 HV Rijswijk Tel. (+31~70) 340~2040. Tx. 31 651 epo ni, Fax: (+31~70) 340~3016	Fischer, W		

International Application No PCT/US 97/04695

	PCT/US 97/04695
Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
WO 97 14407 A (RES TRIANGLE PHARMACEUTICALS ;UNIV TEXAS (US); HENRIKSEN INGE B (U) 24 April 1997 "L": DOCUMENT SO QUOTED FOR ITS' CASTING DOUBT ON THE VALIDITY OF THE CONVENTION-PRIORITY CLAIMED see the whole document	1-4, 6-13, 15-17
US 5 091 187 A (HAYNES DUNCAN H) 25 February 1992	
US 5 364 633 A (HILL RANDAL M ET AL) 15 November 1994	
WO 94 20072 A (PHARMACIA AB ;WESTESEN KIRSTEN (DE); SIEKMANN BRITTA (DE)) 15 September 1994	
·	
	PHARMACEUTICALS ;UNIV TEXAS (US); HENRIKSEN INGE B (U) 24 April 1997 "L": DOCUMENT SO QUOTED FOR ITS' CASTING DOUBT ON THE VALIDITY OF THE CONVENTION-PRIORITY CLAIMED see the whole document US 5 091 187 A (HAYNES DUNCAN H) 25 February 1992 US 5 364 633 A (HILL RANDAL M ET AL) 15 November 1994 WO 94 20072 A (PHARMACIA AB ;WESTESEN KIRSTEN (DE); SIEKMANN BRITTA (DE)) 15

Information on patent family members

International Application No PCT/US 97/04695

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP 0601618 A	15-06-94	US 5336507 AU 662453 AU 5046893 CA 2102267 CZ 9302602 FI 935305 HU 65758 JP 6211646 NO 934204 NZ 250062 SK 139093 US 5470583	B A A A A A A A	09-08-94 31-08-95 23-06-94 12-06-94 15-06-94 12-06-94 28-07-94 02-08-94 13-06-94 27-04-95 07-12-94 28-11-95
EP 0602700 A	22-06-94	US 5326552 AU 664115 AU 4867293 CA 2107165 CZ 9302668 FI 935396 HU 67265 JP 6192131 MX 9306012 NO 934425 NZ 248727 SK 142793 US 5447710	B A A A A A A A A A A	05-07-94 02-11-95 30-06-94 18-06-94 17-08-94 18-06-94 28-03-95 12-07-94 31-01-95 20-06-94 27-04-95 06-07-94 05-09-95
US 5447710 A	05-09-95	US 5326552 AU 664115 AU 4867293 CA 2107165 CZ 9302668 EP 0602700 FI 935396 HU 67265 JP 6192131 MX 9306012 NO 934425 NZ 248727 SK 142793	B A A A A A A A A A A A	05-07-94 02-11-95 30-06-94 18-06-94 17-08-94 22-06-94 18-06-94 28-03-95 12-07-94 31-01-95 20-06-94 27-04-95 06-07-94

Information on patent family members

International Application No PCT/US 97/04695

Patent document	Publication	Patent family	/	Publication
cited in search report	date	member(s)		date
US 5326552 A	05-07-94	AU 664115	5 B	02-11-95
		AU 4867293		30-06-94
		CA 2107165		18-06-94
		CZ 9302668		17-08-94
		EP 0602700		22-06-94
		FI 935396		18-06-94
		HU 67265		28-03-95
		JP 6192131		12-07-94
		MX 9306012		31-01-95
		NO 934425		20-06-94
		NZ 248727		27-04-95
		SK 142793		06-07-94
		US 5447710		05-09-95
WO 9714407 A	24-04-97	AU 7461796	A	07-05-97
US 5091187 A	25-02-92	US 5091188		25-02-92
		AU 7852891		11-11-91
		CA 2078990		27-10-91
		EP 0533690	A	31-03-93
		IN 173056		05-02-94
		MX 25532		01-10-93
		WO 9116068		31-10-91
		US RE35338		24-09-96
*		US 5246707	A	21-09-93
US 5364633 A	15-11-94	EP 0672410	Α	20-09-95
		JP 7323222		12-12-95
		US 5411744	Α	02-05-95
WO 9420072 A	15-09-94	CA 2091152	A	06-09-94
		AU 676279		06-03-97
		AU 6225394		26-09-94
		EP 0687172		20-12 - 95
		FI 954143		19-10-95
		JP 8507515		13-08-96
		NO 953461		06-11-95
		NZ 262541	Δ	24-04-97